




DRAGON JACKET S-1 & S-3

WATER PERMEABILITY TEST RESULTS

WATER VAPOR TRANSMISSION BY ASTM E 96					
SAMPLE THICKNESS (in)	(g/hr)	WVTR (g/hr m ²)	PERMEANCE (g/Pa·s·m ²)	PERMS	
0.02463	-0.0057				
0.01861	-0.0070				
<u>0.01971</u>	<u>-0.0070</u>				
AV= 0.0209	-0.0067	1.4776	2.59 x 10 ⁻⁷	4.53	
± 0.0032	± 0.0007	± 0.154	± 0.27 x 10 ⁻⁷	± 0.57	

DISH #3 HT100F POLYUREA PRODUCT



DISH #2 HT100F POLYUREA PRODUCT

